

TEST EN 12722, 1997-10 - 70°C

Tested sample	Structure	Temperature	Classification
LM08	Matrix	70°C	5
LK55	Matrix	70°C	5
LM17	Matrix	70°C	5
S012	Yosemite	70°C	5
S013	Yosemite	70°C	5

Level 1: Surface distortion and/or blistering

Level 2: Marked change of gloss and/or color


Level 3: Moderate change of gloss and/or color

Level 4: Slight change of gloss and/or color, only visible at certain viewing angles

Level 5: No visible change

Lissone, 25/06/12

Dr Stefano Monti



CLEAF
surfaceresearchlab